

Observation of Well-Ordered Metastable Vortex Lattice Phases in Superconducting MgB_2 Using Small-Angle Neutron Scattering

P. Das,¹ C. Rastovski,¹ T. R. O'Brien,^{1,*} K. J. Schlesinger,^{1,†} C. D. Dewhurst,² L. DeBeer-Schmitt,³ N. D. Zhigadlo,⁴ J. Karpinski,⁴ and M. R. Eskildsen^{1,‡}

¹*Department of Physics, University of Notre Dame, Notre Dame, Indiana 46556, USA*

²*Institut Laue-Langevin, 6 Rue Jules Horowitz, F-38042 Grenoble, France*

³*Oak Ridge National Laboratory, Oak Ridge, Tennessee 37831-6393, USA*

⁴*Laboratory for Solid State Physics, ETH Zurich, CH-8093 Zürich, Switzerland*

(Received 22 December 2011; published 19 April 2012)

The vortex lattice (VL) symmetry and orientation in clean type-II superconductors depends sensitively on the host material anisotropy, vortex density and temperature, frequently leading to rich phase diagrams. Typically, a well-ordered VL is taken to imply a ground-state configuration for the vortex-vortex interaction. Using neutron scattering we studied the VL in MgB_2 for a number of field-temperature histories, discovering an unprecedented degree of metastability in connection with a known, second-order rotation transition. This allows, for the first time, structural studies of a well-ordered, nonequilibrium VL. While the mechanism responsible for the longevity of the metastable states is not resolved, we speculate it is due to a jamming of VL domains, preventing a rotation to the ground-state orientation.

DOI: 10.1103/PhysRevLett.108.167001

PACS numbers: 74.25.Ha, 61.05.fg, 74.25.Wx, 74.70.Ad

Metastable phases of matter are well known, with famous examples including supercooling and superheating of liquids and diamond which is one of the many allotropes of carbon. Metastability is almost exclusively observed in connection with first-order transitions, and is often found in frustrated systems where the energy difference between the states is small. The structure of the vortex lattice (VL) in type-II superconductors is known to be highly sensitive to changes in external parameters such as temperature and magnetic field and can therefore naively be expected to display metastability, for example, in connection with first-order transitions such as the VL melting [1] or the reorientation transition of the rhombic VL found in most superconductors with a fourfold in-plane anisotropy [2]. However, except for phase coexistence in the vicinity of reorientation transitions [3–6], no well-ordered metastable VL phases have been observed to date.

We present extensive small-angle neutron scattering (SANS) studies of the VL in MgB_2 with $\mathbf{H} \parallel \mathbf{c}$ which is found to exhibit an unprecedented degree of metastability. Previous studies of this compound revealed a continuous, field-driven 30° VL rotation bounded by two second-order transitions. The rotation is understood to arise from a competition between sixfold Fermi surface anisotropies with opposite signs on the π and σ bands, coupled with the suppression of the π -band superconductivity by a modest magnetic field [7,8]. The most striking new results are the existence of highly ordered nonequilibrium VL configurations and the observation of hysteresis in connection with a second-order phase transition which we speculate is the result of a jamming-like scenario. As a result, the ground-state VL phase diagram is found to differ significantly from our earlier report as well as theoretical predictions [7,8].

Small-angle neutron scattering (SANS) experiments were performed at the D22 instrument at Institut Laue-Langevin, the HFIR GP-SANS beam line at Oak Ridge National Laboratory and NG3 at the NIST Center for Neutron Research, using a standard configuration with the applied magnetic field parallel to the incoming neutron beam [9]. To achieve diffraction the sample and the magnet were rotated and/or tilted together in order to satisfy the Bragg condition for the VL planes. Complete VL diffraction patterns were obtained by adding the scattering, recorded by a 2D position sensitive detector, from several angles. To resolve closely located VL Bragg reflections, a very tight collimation of the neutron beam was used (D22: 0.06° , GP-SANS/NG3: 0.08° FWHM).

Several different single crystal samples were studied providing consistent results, with only slight variations in the VL transition fields and temperatures. The crystals, with masses in the range 100–200 μg , were grown using isotopically enriched ^{11}B to reduce neutron absorption and were comparable to those used in previous SANS experiments by our group [7,10,11].

Measurements were performed at temperatures between $T = 2$ and 28 K, and in magnetic fields up to $H = 1.9$ T applied parallel to the crystalline c axis. Several different field-temperature histories were employed: Constant field cooled (FC) from a temperature above T_c and field ramped (FR) where H was changed at a constant temperature. Other measurements were performed following a damped, small-amplitude field oscillation applied after either a FC or FR procedure.

Figure 1 shows VL diffraction patterns, obtained at three different places in the mixed state phase diagram of MgB_2 , which summarize the main result of this report. Panels (a)




FIG. 1 (color online). SANS diffraction patterns showing the different triangular VL phases in MgB_2 with $\mathbf{H} \parallel \mathbf{c}$. The orientation of the crystalline a axis is shown in panel (a) and the a^* axis in panel (e). The three columns show the VL configurations at 18 K and 0.5 T [(a) and (d)], 2 K and 0.5 T [(b) and (c)], and 2 K and 1.1 T [(e) and (f)]. In cases where not all VL reflections were rocked through the Bragg condition, symmetry equivalent positions, obtained by mirroring through and/or rotating around $q = 0$, are indicated by open circles. In the high symmetry F and I phases a single-domain VL is observed aligned with Bragg reflections along respectively \mathbf{a} and \mathbf{a}^* . In the intermediate L phase two VL domains orientations, indicated by $2 \times 6 = 12$ peaks, are observed rotated away from \mathbf{a} by an angle φ in opposite directions as shown in panel (f). For each field and temperature the ground state VL is obtained following a damped field oscillation with an initial amplitude of 25 mT.

and (b) were obtained following a FC procedure from a temperature $T > T_c$ to 18 K and then 2 K in a constant field of 0.5 T, and both show VLs oriented with Bragg reflections along the crystalline a axis. In both cases the VL is well-ordered, indicated by very sharp and well-defined Bragg peaks and narrow rocking curves shown in the Supplemental Material [12]. Traditionally such high quality diffraction patterns are taken as an indication that the VL is an equilibrium configuration for the vortex-vortex interaction [4]. However, applying a small-amplitude field oscillation at 2 K causes a transition to a VL phase which is rotated away from the a axis by an angle φ , as shown in panel (c). Here a superposition of scattering from two degenerate domain orientations is observed, corresponding to clockwise and anticlockwise rotations of the VL. The widths of the peaks (radial, azimuthal, longitudinal) stay effectively unchanged. The rotated VL remains robust upon heating to 18 K as shown in (d), but a subsequent field oscillation causes a transition to the a axis aligned phase as in panel (a). Additional measurements showed that in the absence of a field oscillation the rotated VL phase at 0.5 T (d) persists up to the highest measurable temperature of 28 K.

These results show that the ordered VL in MgB_2 exhibits metastability as it is heated or cooled across the equilibrium phase transition which must exist somewhere between 2 and 18 K. Furthermore, it is necessary to induce vortex motion by a small-amplitude field oscillation in order to drive the VL to the ground-state (equilibrium)

configuration. A similar effect is observed at 1.1 T where the field cooled VL is aligned along the a^* axis as shown in panel (e). After a field oscillation, the VL enters the rotated phase (f). In summary, this system presents, for the first time, the opportunity to perform structural studies of a well-ordered, non-ground-state VL. Because of the similarity with the tilted hexatic phases in liquid crystals, we adopt the same naming scheme, denoting the VL phases as F , I and L as indicated in Fig. 1 [13–15].

Figure 2(a) shows a comparison between the VL orientation angle φ , obtained at 2 K following, respectively, a FC and a field ramping (FR) procedure where the magnetic field is changed at the measurement temperature. For fields ≥ 0.2 T the two procedures result in different VL phases. Furthermore, the ground-state VL at this temperature never completes the rotation transition but remains in the L phase, stabilizing at $\varphi \approx 24^\circ$ above 1.2 T. We note that a FR or a FC followed by a field oscillation both achieve the same result. Figure 2(b) shows the field dependence of the FR VL orientation obtained at temperatures in the range 2–20 K. Only for temperatures of 10 K and above does the ground-state VL reach the I phase ($\varphi = 30^\circ$). The ground-state VL configuration is summarized in the phase diagram in Fig. 3. Because of decreasing intensity, it was not possible to determine the phase boundaries above 1.8 T and 20 K. Nonetheless, the constant φ for $H \geq 1.3$ T at both 2 and 5 K seen in Fig. 2 strongly suggests that LI transition is essentially vertical at low temperatures as indicated by the extrapolation in the phase diagram.




FIG. 2 (color online). VL orientation angle as a function of applied field. Panel (a) shows the results of measurements at 2 K following a FC procedure and a zero field cooling followed by a FR. The arrow indicates the FL transition for the ground-state VL. Panel (b) shows the FR VL orientation at temperatures ranging from 2 to 20 K. All lines are guides to the eye.

Likewise, the fact that the L phase can be observed following a FC implies that it extends up to H_{c2} within a narrow field range.

The ground-state VL phase diagram differs markedly from a naive expectation that the effect of the π -band anisotropy, believed to be responsible for the F and L phases, should be largest at low fields (little suppression of π -band superconductivity) and high temperatures (increased thermal mixing of bands) [7,8]. Consequently, one would expect the I phase to occupy the high-field and low-temperature part of the phase diagram in striking contrast to Fig. 3. In particular, the reappearance of the L phase as one follows H_{c2} to lower temperatures is unexpected and does not agree with theoretical predictions [8].

We now return to the metastable VL phases shown in Figs. 1(b), 1(d), and 1(e), noting that the existence of such states in connection with a second-order phase transition is unexpected as shall be discussed in the following. It should be stressed that the present case is not one of a first-order transition broadened by sample inhomogeneities as, for example, observed in connection with the order-disorder transition associated with the peak effect [16]. As pointed out by Zhitomirsky and Dao, the continuous rotation of the VL in MgB_2 with second-order FL and LI transitions




FIG. 3. Ground-state VL phase diagram for MgB_2 with $\mathbf{H} \parallel \mathbf{c}$. The FL transition is indicated by squares and the LI transition by circles. The lines are guides to the eye with dashes indicating extrapolations to higher temperatures and fields. Diamonds indicate measured values of H_{c2} .

shows that the VL free energy as a function of the orientation angle must be given by

$$\delta F = K_6 \cos 6\varphi + K_{12} \cos 12\varphi, \quad (1)$$

with $K_{12} > 0$ [8]. The same free energy expression has been used to model the reorientation transitions observed between tilted hexatic phases in liquid crystals [17], where we note no metastable phases are observed. Figure 4(a) shows the evolution of δF as K_6 is increased from $< -4K_{12}$ to $> 4K_{12}$. In Fig. 4(b) we consider the free energy curves corresponding to the cycle of VL phases in Figs. 1(a)–1(d), which shows that the metastable F phase (b) corresponds to an unstable equilibrium [$d(\delta F)/d\varphi = 0$; $d^2(\delta F)/d\varphi^2 < 0$] while the metastable L phase (d) represents a true nonequilibrium situation [$d(\delta F)/d\varphi \neq 0$]. This implies that the VL metastability cannot be understood from the single-domain free energy thus raising the important question: Which mechanism is responsible for the longevity of the metastable states, preventing them from immediately rotating to the ground state?

A straightforward answer to the above question is that the metastable VLs are held in place by vortex pinning. However, in general metastability is a hallmark of very clean systems, in obvious contrast to such a scenario. More specifically this also seems unlikely given the very low depinning critical current in clean MgB_2 single crystals similar to the ones used in the present work ($< 2 \times 10^3$ A/cm² at 5 K and 0.5 T and decreasing with higher T and H) [18]. Moreover, at 0.5 T the irreversibility line for $\mathbf{H} \parallel \mathbf{c}$ is in the range 8–14 K [18], much below the highest measurable temperature of 28 K, where we still observe a metastable L phase. Finally, the sharp VL Bragg peaks observed in the FC case does not indicate any significant disorder due to vortex pinning in contrast to reports for, e.g., $\text{YNi}_2\text{B}_2\text{C}$ [4–6].




FIG. 4 (color online). Free energy curves for the VL phases in MgB_2 . Panel (a) shows the progression of free energy curves calculated using Eqn. (1) with $K_{12} = 1$ and increasing K_6 . The corresponding ground-state VL phase is indicated by each curve. The FL and LI transitions occur at $K_6 = \pm 4$. Panel (b) shows free energy curves corresponding to the sequence of diffraction patterns at 0.5 T shown in Fig. 1. Solid circles represent ground-state VL configurations while open circles represent metastable phases.

We speculate that the mechanism which sustains the metastable configurations is a jamming of counter-rotated VL domains against one another [19]. In this scenario the VL domains acts as granular entities, preventing each other from rotating to the ground-state orientation. If this is the case a close examination of the metastable F and I phases should find an onset of domain formation, leading to an azimuthal broadening of the VL peaks which would be most visible at higher fields as the resolution improves with H . Such an azimuthal broadening is indeed observed at 2 K and 1.1 T, increasing from a resolution limited $\sim 4^\circ$ in the ground-state L phase to $\sim 7.5^\circ$ in the metastable I phase, as shown in Fig. S3 and discussed in detail in the Supplemental Material. No broadening is expected or observed in the metastable L phase. Further studies are needed to fully explore this jamming hypothesis. A key question in this regard will be to investigate the robustness of the VL domain boundaries necessary to prevent rotation. Theoretically, recent work by Deutsch and Shapiro considered domain boundaries in a square VL [20]. Such studies should be extended to investigate how this affects the VL configuration.

Before concluding, we note that SANS studies of the VL in UPt_3 used a temperature quenching technique to infer information about the superconducting A phase which exist just below H_{c2} in this material [21]. In this case a rotated VL identical to the L phase was interpreted as originating from a particular order parameter symmetry. Our results on MgB_2 , which does not have the exotic pairing symmetry of UPt_3 , are qualitatively similar, suggesting that this interpretation may have to be reconsidered.

In summary, we discovered a high degree of metastability in the MgB_2 VL, which allows measurements in non-equilibrium configurations. The ground-state VL phase diagram was determined and found to differ substantially from theoretical predictions. We speculate that a jamming scenario is responsible for the VL metastability.

We acknowledge discussions with X. Cheng, G. Crawford, R. Cubitt, E.M. Forgan, M. Gingras, M. Konczykowski, C. Olson Reichhardt, and C. Reichhardt, and technical assistance at CNR by J.G. Barker and A.J. Jackson. This work was supported by the Department of Energy, Basic Energy Sciences under Grant No. DE-FG02-10ER46783. T.R. O'B recognizes support from the Notre Dame Glynn family honors program, the College of Science Undergraduate Research Fund and the ND REU program (National Science Foundation grant PHY05-52843). K. J. S. recognizes support from the Notre Dame Institute for Scholarship in the Liberal Arts. N.D.Z. and J.K. was supported by the National Center of Competence in Research MaNEP (Materials with Novel Electronic Properties). The Research at Oak Ridge National Laboratory's High Flux Isotope Reactor was sponsored by the Scientific User Facilities Division, Office of Basic Energy Sciences, U.S. Department of Energy. We acknowledge the support of the National Institute of Standards and Technology, U.S. Department of Commerce, in providing neutron research facilities used in this work. This work utilized facilities supported in part by the National Science Foundation under Agreement No. DMR-0944772.

Note added in proof.—We recently learned that K. Machida and collaborators have been able to calculate the progression of ground-state VL phases in MgB_2 along H_{c2} , starting from first principles band structure calculations [22].

*Present address: Department of Electrical and Computer Engineering, University of Illinois at Urbana-Champaign, Urbana, IL 61820, USA.

†Present address: Department of Physics, University of CA, Santa Barbara, CA, 93106, USA.

‡eskildsen@nd.edu

[1] E. Zeldov, D. Majer, M. Konczykowski, V.B. Geshkenbein, V.M. Vinokur, and H. Shtrikman, *Nature (London)* **375**, 373 (1995).

- [2] K. M. Suzuki, K. Inoue, P. Miranovic, M. Ichioka, and K. Machida, *J. Phys. Soc. Jpn.* **79**, 013702 (2010).
- [3] M. R. Eskildsen, A. B. Abrahamsen, D. Lopez, P. L. Gammel, D. J. Bishop, N. H. Andersen, K. Mortensen, and P. C. Canfield, *Phys. Rev. Lett.* **86**, 320 (2001).
- [4] S. J. Levett, C. D. Dewhurst, and D. McK. Paul, *Phys. Rev. B* **66**, 014515 (2002).
- [5] C. D. Dewhurst, S. J. Levett and D. McK. Paul, *Phys. Rev. B* **72**, 014542 (2005).
- [6] J. S. White, R. W. Heslop, A. T. Holmes, E. M. Forgan, V. Hinkov, N. Egetenmeyer, J. L. Gavilano, M. Laver, C. D. Dewhurst, R. Cubitt, and A. Erb, *Phys. Rev. B* **84**, 104519 (2011).
- [7] R. Cubitt, M. R. Eskildsen, C. D. Dewhurst, J. Jun, S. M. Kazakov, and J. Karpinski, *Phys. Rev. Lett.* **91**, 047002 (2003).
- [8] M. E. Zhitomirsky and V.-H. Dao, *Phys. Rev. B* **69**, 054508 (2004).
- [9] M. R. Eskildsen, *Front. Phys.* **6**, 398 (2011).
- [10] J. Karpinski, M. Angst, J. Jun, S. M. Kazakov, R. Puzniak, A. Wisniewski, J. Roos, H. Keller, A. Perucchi, L. Degiorgi, M. R. Eskildsen, P. Bordet, L. Vinnikov, and A. Mironov, *Supercond. Sci. Technol.* **16**, 221 (2003).
- [11] D. Pal, L. DeBeer-Schmitt, T. Bera, R. Cubitt, C. D. Dewhurst, J. Jun, N. D. Zhigadlo, J. Karpinski, V. G. Kogan, and M. R. Eskildsen, *Phys. Rev. B* **73**, 012513 (2006).
- [12] See Supplemental Material at <http://link.aps.org/supplemental/10.1103/PhysRevLett.108.167001> for details.
- [13] G. S. Smith, E. B. Sirota, C. R. Safinya, and N. A. Clark, *Phys. Rev. Lett.* **60**, 813 (1988).
- [14] M. R. Fisch and S. Kumar, in *Liquid Crystals: Experimental Study of Physical Properties and Phase Transitions*, edited by S. Kumar (Cambridge Univ. Press, Cambridge, 2001), p. 1.
- [15] In liquid crystals SmF, SmL and SmI are smectic phases with long range orientational (but not positional) order. While CrH and CrK are used for the crystalline phases corresponding to SmF and SmI, respectively, there is no equivalent name for the SmL phase. We have therefore chosen to use *F*, *L*, *I* for the VL phases in MgB₂.
- [16] G. Jung, Y. Paltiel, E. Zeldov, Y. Myasoedov, M. L. Rappaport, M. J. Higgins, and S. Bhattacharya, *Lect. Notes Phys.* **688**, 109 (2006).
- [17] J. V. Selinger and D. R. Nelson, *Phys. Rev. A* **39**, 3135 (1989).
- [18] M. Zehetmayer, M. Eisterer, J. Jun, S. M. Kazakov, J. Karpinski, A. Wisniewski, and H. W. Weber, *Phys. Rev. B* **66**, 052505 (2002).
- [19] A. J. Liu and S. R. Nagel, *Annu. Rev. Condens. Matter Phys.* **1**, 347 (2010).
- [20] E. Deutsch and B. Y. Shapiro, *Supercond. Sci. Technol.* **23**, 125004 (2010).
- [21] A. Huxley, P. Rodiere, D. McK. Paul, N. van Dijk, R. Cubitt, and J. Flouquet, *Nature (London)* **406**, 160 (2000).
- [22] T. Hirano, M. Ichioka, and K. Machida, private communication.